

## Technical Data

# MPDiol® Glycol


## Elastomer Compatibility and Plastic Resistance

### General

The data provided here addresses the ability of the elastomer seal material or plastic to resist the contacting fluid. Many factors can contribute to performance in actual field conditions. For instance, some elastomer compounds shrink instead of swell in certain fluids. This phenomenon, coupled with high compression set, can result in seal leakage following thermal or pressure cycling. Seals behave differently in dynamic applications than in static conditions. Whenever in doubt, test for suitability before using.

### Physical Properties

Chemical Name	2-Methyl-1,3-Propanediol
CAS Number	2163-42-0
Molecular Weight (g/mole)	90.1
Boiling Point (760 mm Hg)	212°C
Flash Point (Closed cup)	127°C
Specific Gravity @25°/25°C	1.015
Evaporation Rate (n-BuAc = 100)	<0.1
Vapor Pressure (760 mm Hg @ 20°C)	0.04



Structure of MPDiol® Glycol

### MPDiol Elastomer Compatibility

Elastomer	% Weight Change	% Area Change	Color Change
Natural Rubber	-3.09	-7.2	Green
Neoprene	-2.11	-3.96	Brown
Butyl	-0.50	-1.99	None
Silicone	0.07	0	None
EPDM	-0.70	0	Lt. Yellow
Viton	-0.29	0	None
PVC	-12.24	-13	None
Mylar	0	0	None
Hypalon	0.49	0	Yellow
BUNA	-1.27	-1.99	Brown
Teflon	0.04	0	None
Nylon	0.40	0	None
Kalrez	-0.02	0	None

The average % change in weight and area, and the color change were taken after 6 weeks at 120°F.

### Chemical Resistance of Plastic and Elastomers

For the following, chemical resistance was measured after 6 weeks at 50°C.

Elastomer	Resistant
ABS/Nitrile/Buna	No
Neoprene	No
PTFE	Yes
PVC	No
Viton	Yes

## Technical Data

# MPDiol® Glycol

## Elastomer Compatibility and Plastic Resistance

For the following, chemical resistance was determined by experience in actual field conditions at ambient temperature.

Elastomer	Resistant
Irradiated Polyethylene	Yes
Kalrez	Yes
Mylar	Yes
Nylon	Yes
Silicone	Yes
Teflon	Yes
Viton	Yes

ABS - Acrylonitrile Butadiene Styrene

PTFE - Poly Tetra Fluoro Ethylene (Teflon)

PVC - Poly Vinyl Chloride

Viton - Vinylidene fluoride / hexafluoropropylene copolymer

Neoprene - Chloroprene polymer

Butyl - Isobutylene / Isoprene Copolymer

This information is believed to be accurate as of the date of publication. It is the sole responsibility of the customer to determine whether the product is appropriate and suitable for the customer's specific use. Specific end uses may require approval by appropriate regulatory agencies. Lyondell Chemical Company makes no warranties, express or implied, regarding the product or information contained therein. The applicable Material Safety Data Sheet should be reviewed by customer before handling the Lyondell Chemical product. Lyondell Chemical Company disclaims any liability for infringement of any patent by reason of customer's use of any Lyondell Chemical Company products in combination with other materials or in any process.

World Headquarters  
Lyondell Chemical Company  
1221 McKinney  
Houston, TX 77010  
Tel (713) 652-7200  
Toll-free (888) 777-0232  
MSDS Hotline: (800) 700-0946

European Headquarters  
Lyondell Chemical Europe, Inc.  
P. O. Box 2416  
3000 CK Rotterdam  
The Netherlands  
Tel (31) 10 275-5500  
Tel (33) 3 44 24 92 05 (tech svc)

Lyondell South America  
Av Roque Petroni Jr,  
999, cj 123  
Sao Paulo, SP 04707-910  
Brazil  
Tel (55) 11-5185-9300

Asian Headquarters  
Lyondell Asia Pacific, Ltd.  
41<sup>st</sup> Floor – The Lee Gardens  
33 Hysan Avenue  
Causeway Bay, Hong Kong  
Tel (852) 28822-668  
Tel (33) 3 44 24 92 05 (tech svc)