

U.S. SALES SPECIFICATION



Material Number: 499250
Product Name: T-HYDRO® Solution
Chemical Name: Tertiary Butyl Hydroperoxide Solution

Test Description	Specification Limits		Unit of Measure	Test Method
	Minimum	Maximum		
Restricted Stock?				
Current Quality Grade	Conforming to Specification			
Vehicle Type	Report			
Vehicle ID	Report			
Miscellaneous Text	Report			
Lot Number	Report			
Inspection Lot	Report			
Manufacturing Date	Report			
Active Oxygen	12.2	12.6	weight %	HOC 0415
Assay as TBHP	69.00	71.00	weight %	HOC 0415
DTBP (Dialkyl Peroxides)		0.08	weight %	HOC 0515
Ketones		0.18	weight %	HOC 0515
Other Hydroperoxides		1.00	weight %	HOC 0515
Other Organics		0.40	weight %	HOC 0515
TBA		0.50	weight %	HOC 0515
Water (by difference)	Report		weight %	HOC 0514
Color, Pt-Co		15	APHA Color	LCC2643
Water Phase, Free		0.7	volume %	HOC 0414

Issue or Revision Date: 07/24/2008

Spec Version Number: 6

Material Number: 8728 11669 499250 499251 499252 499347 499355 499357 499358

This report has been generated from our business computing system and lists those properties our company evaluates in conducting batch selection decisions. This report may also contain typical properties and their expected values. This report may not cover your entire specification, which may include requirements for packaging, shipping, storage, delivery, etc.

The information in this bulletin is believed to be accurate and current as of the date of publication. It is the sole responsibility of the customer to determine whether the product is appropriate and suitable for the customer's specific use. Lyondell Chemical Company and its affiliates and subsidiaries make no warranties, express or implied, regarding the product or any information contained herein.

The applicable Material Safety Data Sheet should be reviewed before handling the Lyondell product. Lyondell Chemical Company and its affiliates and subsidiaries disclaim any liability against infringement of any patent by reason of customer's use of any Lyondell Chemical Company products in combination with other materials or in any process.

The information on this report is valid as of: 07/24/2008 M