



Aquathene™

AQ120000

Ethylene Vinylsilane Copolymer

Wire and Cable Grade

Melt Index 1.5 Density 0.923

Applications

AQUATHENE AQ120000 is an ethylene vinylsilane copolymer designed for use in low voltage, power cable applications. This natural resin can be crosslinked, by exposure to moisture after extrusion with an appropriate catalyst.

Processing Techniques

AQ120000 can be extruded using conventional extrusion equipment. For example, AQ120000 has been extruded successfully using a 2 .5", 20:1 extruder equipped with a Maddock mixing screw under the following conditions.

| Extruder Zone | Temperature | Extruder Zone | Temperature |
|---------------|---------------|---------------|---------------|
| Feed | 135°C / 275°F | Zone 4-X | 160°C / 320°F |
| Zone 2 | 145°C / 293°F | Adapter | 165°C / 329°F |
| Zone 3 | 155°C / 311°F | Die | 170°C / 338°F |

Crosslinking of the total system, AQ120000 and an appropriate crosslinking catalyst such as AQUATHENE [CM04482](#) or [CM04483](#) occurs after the materials are mixed during extrusion and exposed to moisture. Crosslinking can be achieved by exposure to steam, immersion in hot water or storage at ambient conditions. The time required to achieve crosslinking depends on the catalyst masterbatch and temperature of the moisture. Because conditions can vary considerably, contact your Equistar sales representative for detailed recommendations.

AQ120000 should be stored separately from the crosslinking catalyst masterbatch until extrusion. This resin can be stored in bulk for several months without special packaging and should not require drying prior to extrusion.

Typical Properties

| Property* | Nominal Value | Units | ASTM Test Method |
|------------------------|---------------|-------------------|------------------|
| Melt Index | 1.5 | g/10 min | D 1238 |
| Density | 0.923 | g/cm ³ | D 1505 |
| Tensile Stress @ Break | 1920 (13.3) | psi (MPa) | D 638 |
| Elongation @ Break | 720 | % | D 638 |

*All properties determined from compression molded plaques.

The values listed for physical electrical properties are nominal values only and are subject to normal variations consistent with the test methods and/or variations found acceptable to the industry.

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at 800.700.0946.

™Aquathene is a registered trademark of Equistar Chemicals, LP.



Lyondell Chemical Company
1221 McKinney, Suite 700
P.O. Box 2583
Houston, Texas 77252-2583
800.615.8999
<http://www.lyondell.com>