

Petrothene

# GA837091

Medium Density Polyethylene

Wire and Cable Grade

Melt Index 0.75 Density 0.9345



## Applications

*Petrothene* GA837091 is a broad molecular weight, medium density resin designed for use as a base resin in wire and cable jacketing. An antioxidant has been added to ensure thermal stability.

## Regulatory Status

GA837091, like other thermoplastic polyolefin compounds, can be extruded as wire a cable jacketing using a conventional extruder. Below are suggested extrusion conditions for GA837091 These conditions are intended as general guidelines only and are not optimum values, since manufacture conditions, such as extruder type and size, affect the processing of thermoplastic compounds. For exact recommendations, contact your Equistar sales representative.

## Suggested General Extrusion Conditions

Extruder Zone	Temperature Range	Extruder Zone	Temperature Range
Feed	310°-325°F (154°-163°C)	Zone 4-X	400°-425°F (204°-218°C)
Zone 2	350°-380°F (177°-193°C)	Adapter	400°-425°F (204°-218°C)
Zone 3	380°-410°F (193°-210°C)	Die	400°-425°F (204°-218°C)

## Industry Specifications

GA837091 meets the requirements of the following: ASTM D 1248, Type II, Category 4, Class A, Grade E9. Federal LP390C, Type II, Class M, Category 4, Grade 2.

## Typical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index	0.75	g/10 min.	D 1238
Density	0.9345	g/cc	D 1505
Tensile Strength @ Break	4,100 (28.3)	psi (MPa)	D 638
Tensile Stress @ Yield	2,400 (16.5)	psi (MPa)	D 638
Elongation @ Break	790	%	D 638
Dielectric Constant @ 1 MHz	2.31		D 1531
Dissipation Factor @ 1 MHz	0.00006		D 1531
ESCR, 10% Igepal®	>1,000	hours	D 1693
Low Temperature Brittleness, F <sub>50</sub>	<-76	°C	D 2240

For further information on resins and compounds for wire and cable, contact your Equistar sales or technical service representative.

® Igepal is a registered trademark of the Rhône-Poulenc Co., Inc.

---

Equistar Chemicals, LP, is a member of the LyondellBasell group companies.

*Petrothene* is a trademark owned or used by one of the LyondellBasell family of companies. Trademark *Petrothene* is registered in the U.S. Patent and Trademark Office.

**Before using a product sold by one of the LyondellBasell family of companies, users should make their own independent determination that the product is suitable for the intended use and can be used safely and legally. SELLER MAKES NO WARRANTY; EXPRESS OR IMPLIED (INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE) OTHER THAN AS SEPARATELY AGREED BETWEEN THE PARTIES IN WRITING. This product(s) may not be used in the manufacture of any US FDA Class III Medical Device or Health Canada Class IV Medical Device and may not be used in the manufacture of any US FDA Class II Medical Device or Health Canada Class II or Class III Medical Device without the prior written approval by Seller of each specific product or application.**

Users should review the applicable Material Safety Data Sheet before handling the product.

Equistar Chemicals, LP  
1221 McKinney, Suite 700  
P. O. Box 2583  
Houston, Texas 77252-2583  
(800) 615-8999  
[www.lyondellbasell.com](http://www.lyondellbasell.com)