

Petrothene®

KR92828

High Density Polyethylene

Wire and Cable Grade

Melt Index 0.17 Density 0.955

Applications

PETROTHENE KR92828 is a high molecular weight, high density polyethylene-based compound designed for use in jacketing, conduit or wire insulation. KR92828 contains a carbon black content of 2.5%. Antioxidant has been added to ensure thermal stability during processing.

Processing Techniques

KR92828, like other thermoplastic polyolefin compounds, can be extruded as wire or cable insulation using a conventional extruder. Below are suggested extrusion conditions for KR92828. These conditions are intended as general guidelines only, and are not optimum values, since manufacturing variables such as extruder type and size have an effect on processing of thermoplastic compounds.

Suggested General Extrusion Conditions

Extruder Zone	Temperature Range	Extruder Zone	Temperature Range
Feed	300°-325°F (149°-163°C)	Adapter	475°-500°F (246°-260°C)
Zone 2	350°-400°F (177°-204°C)	Die	475°-500°F (246°-260°C)
Zone 3	375°-400°F (191°-204°C)	Melt Temperature	475°-500°F (246°-260°C)
Zone 4-X	460°-500°F (238°-260°C)		

Industry Specifications

KR92828 meets the requirements of the following: Federal LP390C Type III, Class H, Category 5, Grades 1 and 2; ASTM D 1248, Type III, Class C, Category 5, Grades J4 and E10.

Typical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index	0.17	g/10 min.	D 1238
Density	0.955	g/CM ³	D 1505
Tensile Strength @ Break	4,600 (31.6)	psi (MPa)	D 638
Tensile Stress @ Yield	2,800 (19.2)	psi (MPa)	D 638
Elongation @ Break	800	%	D 638
Tensile Modulus (1% Secant)	77,000 (531)	psi (MPa)	D 638
Flexural Modulus (1% Secant)	110,000 (760)	psi (MPa)	D 780
Hardness, Shore D	65		D 2240
Low Temperature Brittleness, F ₅₀	<-76	°C	D 746
ESCR, 10% Igepal®	>1,000	hours	D 1693
Dielectric Constant @ 1 MHz	2.50		D 1531
Dissipation Factor @ 1 MHz	0.0002		D 1531
Dielectric Strength	550	V/mil	D 149
Volume Resistivity	2x10 ¹⁷	Ohm-cm	D 257
Carbon Black Content	2.60	%	
Absorption Coefficient	440		D 3349
Linear Coefficient of Thermal Expansion @ 23°C	1.50 x 10 ⁻⁴	in/in/°C	D 696

® Igepal is a registered trademark of the Rhône-Poulenc Co., Inc.

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at 800.700.0946.

®Petrothene is a registered trademark of Equistar Chemicals, LP.



Lyondell Chemical Company
1221 McKinney, Suite 700
P.O. Box 2583
Houston, Texas 77252-2583
800.615.8999
<http://www.lyondell.com>