

**Technical Data Sheet**  
**Premi-Glas 2207-22 CR-SX**  
 Engineered Composites



**Product Description**

Glass Fiber reinforced Polyester SMC suitable for electrical, flame retardant and HVAC applications.

**General**

Material Status	• Commercial: Active		
Availability	• North America	• South America	
Filler / Reinforcement	• Glass Fiber and Mineral Filler		
Features	• UL Recognized – File E69414 • UL94-5VA @1.5mm	• Non-Halogen FR Technology • Pigmentable	• (f1) – Suitable for outdoor use
Processing Method	• This SMC product is generally intended to be compression molded in matched metal molds, typically at 300°F (150°C) and 500 to 1,000 psi (35-65 BAR) molding pressure. Strength values may be affected by the molding process.		
Resin	• Unsaturated Polyester		

Physical	Typical	Unit	Test Method
Density	1.85 – 1.95	g/cm <sup>3</sup>	ASTM D792
Mold Shrinkage (RT mold/RT part)	0.001 – 0.0025	in/in	ASTM D955
Mechanical (As Molded)	Typical	Unit	Test Method
Tensile Modulus	2.0E+6 (12)	psi (GPa)	ASTM D638
Tensile Strength	10,000 (70)	psi (MPa)	ASTM D638
Flexural Modulus (RT)	1.7 E+6 (12)	psi (GPa)	ASTM D790
Flexural Strength	30,000 (210)	psi (MPa)	ASTM D790
Impact	Typical	Unit	Test Method
Izod Notched Impact Strength	16 (850)	ft-lb/in (J/m)	ASTM D256
Thermal	Typical	Unit	Test Method
UL RTI, Electrical	266 (130)	°F (°C)	UL 746C
UL RTI, Mechanical, with Impact	266 (130)	°F (°C)	UL 746C
UL RTI, Mechanical, without Impact	266 (130)	°F (°C)	UL 746C
Flammability	Typical	Unit	Test Method
Flammability	Pass 0.0060 (1.50)	in (mm)	UL94 5VA, V0
Electrical	Typical	Unit	Test Method
Dielectric Strength	460 (16)	Volts/mil (kV/mm)	ASTM D149
Arc Track Resistance	180+	seconds	ASTM D495
Comparative Tracking Index	600	volts	ASTM D2303

**Technical Data Sheet**  
**Premi-Glas 2207-22 CR-SX**  
Engineered Composites



**Notes**

These are typical property values not to be construed as specification limits.

**Processing Techniques**

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

**Company Information**

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2019

**Disclaimer**

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

**Trademarks**

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.